

PRODUCT DATA SHEET

Ganzlin AP - CGL

Area of application:

Weather- and light-resistant polyester powder coating for special industrial applications that require an increased chemical resistance or corrosion protection.

Characteristics:

Polyester powder for manufacturing glossy paint films with excellent flow and covering characteristics as well as high elasticity, increased corrosion protection and enhanced chemical resistance, in particular at higher temperatures.

Colour setting:

According to the customer's requirements, with only carefully selected and tested pigments being used in order to ensure a high light and weather resistance.

Pretreatment:

Depending on the requirements with regards to the final product's adhesion and corrosion resistance and the quality of the surface/substrate, the following options are available:

Steel: degreasing, blasting, iron or zinc phosphate

Aluminium: degreasing, blasting, passivating or chromalising according to DIN 50939 and/or suitable chrome-free pretreatment

Galvanised substrates: degreasing, blasting, zinc phosphate or chromalising and/or suitable chrome-free pretreatment

Processing:

Electrostatic coating (EPS) at a processing voltage of 30 to 100 kV; or electrokinetic coating (tribo-charging). The relevant **safety instructions** (BGV D25, VDE and VDM guidelines) and our EU safety data sheet must be observed and followed.

Please note that the minimum layer thickness for a sufficient hiding power is depending on the colour shade. A corresponding layer thickness recommendation specified according to the VdL-RL 10 can be provided upon request.

Stoving conditions according to DIN 55990-4:

15 – 20 min. at 160 °C object temperature

8 – 12 min. at 180 °C object temperature

Shelf life:

6 months from delivery subject to dry storage at temperatures not exceeding 25°C and without exposure to radiator heat and sunlight!

PRODUCT SPECIFICATIONS:

The test results have been measured at a layer thickness of $70 \pm 10 \mu\text{m}$ on a steel test panel of 0.8 mm covered with a zinc phosphate layer.

Density	DIN EN ISO 2811-1	ca. 1.6 g/cm^3 (depending on colour shade)
Gloss	DIN EN ISO 2813 Angle of 60°	85 ± 10
Cross-cut adhesion test	DIN EN ISO 2409	Gt 0A
Bending test	DIN EN ISO 1519	$\leq 5 \text{ mm}$
Erichsen cupping test	DIN EN ISO 1520	$> 5 \text{ mm}$
Buchholz hardness	DIN EN ISO 2815	> 80
Impact Test	ASTM D 2794	$> 80 \text{ inchpound}$
Weather resistance (QUV, 200 h)	DIN EN ISO 11507	Relative residual gloss (60°) $> 50\%$
Light fastness	DIN 54004	≥ 7
Salt spray test	DIN EN ISO 9227	No blistering after 500 h and under-corrosion $\leq 1 \text{ mm}$
Condensate constant climate	DIN EN ISO 6270-1	No blistering after 500 h and under-corrosion $\leq 1 \text{ mm}$
Condensate alternating climate	ISO 3231 0,2 l SO_2	No blistering after 20 cycles and under-corrosion $\leq 1 \text{ mm}$

Packaging:

15 kg polyethylene bag in disposable cardboard box

The written information in our product specification sheet is provided according to the best of our knowledge and the current state of scientific and practical knowledge. It does not give rise to any legal contract relationship and no secondary obligation in connection to the purchase agreement.

The information contained herein does not exempt the user from his/her obligation to assess the product's suitability for the intended purposes. Our liability is solely subject to our sales and delivery conditions.